

FORMWORK PLYWOOD

PRO FORM

PRO FORM is TEKCOM's formwork plywood with enhanced stability and serviceability, which promise a consistency (alignment) of casting, and is suitable for exposed concrete area.

- Cost-effective for big projects
- For high requirement of concrete surface
- Meet the number of pours as expected



LEGAL SOURCE

Wood Materials

Legally sourced plantation wood

Bonding & Formaldehyde Emission (FE)

Class 3 | EN 636:2003 E1 | EN 717-2-1995

Panel Construction

Water Proof bonding with special underlay Panel density: ≥ 630kg/m³ | EN 323:1993 Moisture content: ≤ 12%, leaving mill | EN 322:1993

Panel Surface & Performance

130 grams/m² of black-brown phenolic surface film (PSF) on both sides Alkalinity resistance | AS 6669-2016 Good wear resistance (>300 revolutions on Taber test)

Standard Sizes

1,220 x 2,440 mm, 1,250 x 2,500 mm, or cut-to-size as buyer's request Size tolerance (width/ length): 1.0 mm | EN 324-1:1993 Squareness tolerance: 1.0 mm/m | EN 324-2:1993

Standard Thicknesses

12mm, 15mm, 17mm, 18mm, 21mm Thickness tolerance according to EN 315:2000 standard

Origin

Made in Vietnam



Mechanical Properties

Parallel to the width of panel	N/mm²	50	EN 310:1993
Parallel to the length of panel	N/mm²	30	
Mean modulus of elasticity	/		
Mean modulus of elasticity Parallel to the width of panel	/ N/mm²	5,000	EN 310:1993

Edge Color

Edges of PRO FORM panel are painted black or gray.

Packaging

Panels are packed in crates with metal/plastic straps, suitable for loading/unloading by forklifts.

Thickness	Crates per container (*)	Cubic meter per container	Maximum net weight
12 mm	14		28.50
15 mm	14	40	
17 mm	14	40	metric tons (**)
18 mm	14		

(*) TEKCOM always loads the materials in 40'HC containers (FCL). (**) In case of different regulation, payload shall be adjusted accordingly.

Pouring Number

PRO FORM is designed for use up to 20 times (2 sides, whole piece).

However, the actual number will also be affected by different factors such as storage conditions, construction methods, concrete components, as well as types of concrete and additives used during construction.

Suitability for Use and Warranty

Nothing herein constitutes a warranty expressed or implied, including any warranty of merchantability of fitness for use, nor is protection from any law or patent to be inferred.

The exclusive remedy for all claims is replacement of materials. Contact the sales office for a copy of the complete TEKCOM Terms and Conditions of Sale.

Other Conformities & Compliances

In case FSC certificate or others are required, contact the sales team for further information.

Warnings:

This product will generate wood dust from sawing, sanding, or shaping.

Material safety data sheets are available upon request.

Good Site Practices



Appropriate Conditions of Storage

Store panels in a dry, clean, well-ventilated, roofed area. Avoid extreme temperature and moisture. Panels must not be placed in contact with the ground. Separate crates from each other with clean, dry and strong spacers of uniform thickness, suitable for loading/unloading by forklifts.



Standard Tools

Panels should be cut, shaped and drilled by using standard wood-working tools. Recommended blade diameter ~ 350 mm, thickness \sim 3.5 mm, number of teeth > 100, and rotational speed 3,000 - 3,600 rpm.



Edges & Holes Sealing

Seal resulting raw edges, holes, and all damaged areas with appropriate water-resistant/ proof paint.



Avoidance of Falls or Drops

Workers at site need to handle (carry, install, remove, etc.) panels properly and do not drop or let them fall from high levels or directly hit other materials or the ground.



Application of Release Agent.

Even though the PSF overlay contains a certain amount of release agent, it is necessary that panels should be coated with suitably approved oil to ensure a cleaner and easier striking, as well as reusage.



Reverse Side Fastening

Panels should be fastened to formwork support components from the reverse side with screws. Shank nails are no recommended.



Cleaning after Use

Formwork plywood panels should be cleaned with water after use to remove concrete residues and other sticking materials on their surface. Suitable care is required to avoid damaging panels.



Recycling and end of the lifespan use

At the of their lifespan the panels can be chipped and used in bioenergy production at your local power plant.

Headquaters - Binh Duong 1 Factory

Lot M1-M2-M7-M8, N2-N3 Street, Nam Tan Uyen Expansion IP, Hoi Nghia Hamlet, Tan Uyen Town, Binh Duong Province,

Office Address - Binh Duong 2 Factory

Lot A1-A2-A3-A4-A5, N5 Street, Nam Tan Uyen Expansion IP, Hoi Nghia Hamlet, Tan Uyen Town, Binh Duong Province, Vietnam.

info@tekcom.vn | (+84) 977 668 000

